

Products Characteristics

- High quality zinc coating with more than 90% zinc share in the dry film
- Cathodic corrosion protection for all bare metals providing resistance to the highest demands against corrosion.
- Resistant to heats of up to 350°C
- Fast drying
- Highly suitable for welding seams
- Resistant to petrol, chemicals and weather influences

Physical and chemical data

Product Type	Epoxyester
Coverage	1.56 - 2.19m ² per 500ml
Drying times	Dust Free 10 - 15 minutes Touch Dry 20 - 30 minutes Overcoatable after 24 hours Resistant to heat after 8 - 12 hours
The drying time depends on temperature, humidity and the thickness of the applied coat.	

Surface Preparation

- The surface must be free from all contamination including rust, grease and moisture.
- Before application, ensure that the mixing balls in the aerosol are moving freely as this ensures that the zinc content is being physically mixed into the paint.

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.



DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.